

PRODUCT CODE: DPU022	COMMERCIAL NAME: D-POWER PU BASECOAT WHITE 22
DESCRIPTION: PU Basecoat White 22	

PROPERTIES

Recommended for / Main area of application	Polyurethanic white sealer specific for MDF with excellent filling properties, excellent covering properties and good sanding properties. It is suitable for the overapplication with polyurethanic glossy varnish. Suggested to do bathroom furniture, kitchens, wardrobes, doors for interior. Suitable for MDF and every kind of wood.
Application Method	By spraygun, airless
Shelf life	24 months

APPLICATION PROPERTIES

PHISICAL PROPERTIES

Quantity	180 - 220 gr/mq	Viscosity	40" +/- 5" DIN 8
Vertical Stability	-	Solid Content	76 +/- 3%
Cathalysis	HAR1811 30% by weight; 50% by volume	Specific Weight	1,480 +/- 0,050 Kg/Lt
Dilution	THIN4000 20-30% by volume	Glossy	-
Pot Life	> 3 h (catalysed at 50% with B180E and thinned at 20% with P730E)	Ph	-

GENERAL INFORMATION

Drying at 20° C		Oven Drying	
Dust Free	10'	Time for Flash Off	-
Touch Free	60'		
Sanding	3 - 4 h	Time for drying	-
Overcoating	8 - 12 h		
Stackable	6 h	Time for cooling	-

FOR INDUSTRIAL USE ONLY Data shown are mean values and cannot be construed as product specifications. Users are advised to make their own tests to determine the suitability of products for their own purposes.

WA: TWENTY TWO SERVICES P/L **Tel** (08) 9206 0220
VIC: CROMA COATINGS VICTORIA **Tel** (03) 9768 2312

NSW: CROMA COATINGS **Tel** (02) 9533 9122
QLD: CROMA COATINGS QUEENSLAND **Tel** (07) 3386 1000



TECHNICAL DATA SHEET

Release: 0

Date: 20/03/2020

RECOMMENDED APPLICATION PROCESS

Apply by spraygun 180-220 gr/mq of DPU022 - D-POWER PU BASECOAT WHITE 22, catalysed at 30% by weight with HAR1811 - D-POWER PU HARDENER 811 and thinned at 20%.
After 40 - 60 minutes apply a second coat of the sealer prepared as above.
The following day sand with sandpaper 220-400 and apply a coat of polyurethane topcoat.

NOTES	User is responsible to make the application of the product in a place with an adequate air-recycle and on respecting of all hygienic and safety regulations.
--------------	--

STORAGE	Containers must be stored tightly closed in a well-ventilated place with temperatures between 5° C and 35° C.
----------------	---

FOR INDUSTRIAL USE ONLY Data shown are mean values and cannot be construed as product specifications. Users are advised to make their own tests to determine the suitability of products for their own purposes.

WA: TWENTY TWO SERVICES P/L **Tel** (08) 9206 0220
VIC: CROMA COATINGS VICTORIA **Tel** (03) 9768 2312

NSW: CROMA COATINGS **Tel** (02) 9533 9122
QLD: CROMA COATINGS QUEENSLAND **Tel** (07) 3386 1000